
Description:	A biocide-free spray, Ecopower Prop is used as a coating for propellers and outdrives. This coating makes it difficult for fouling to fully attach thus making it easy to dislodge and remove when cleaning. Advanced binder technology controls the self-renewing effect throughout the season, without paint build-up.
Availability:	Part of European Yacht assortment. Local availability subject to confirmation.
PHYSICAL CONSTANTS:	
Shade nos/Colours:	19990/ Black.
Finish:	Semi-flat
Volume solids, %:	28 ± 1
Theoretical spreading rate:	1.3 m ² / 500 ml spray can - 25 micron/1 mils
Flash point:	Highly flammable.
Specific gravity:	1.2 kg/litre [10 lbs/US gallon]
Dry to touch:	20 minute(s) , 20°C/68°F 40 minute(s) , 10°C/50°F
VOC content:	629 g/l [5.2 lbs/US gallon]
Shelf life:	5 years
	<i>The physical constants stated are nominal data according to the HEMPEL Group's approved formulas.</i>
APPLICATION DETAILS:	
Application method:	Spray can
Cleaning of tools:	HEMPEL'S THINNER 808 (No 3) 08081
Indicated film thickness, dry:	25 micron [1 mils]
Indicated film thickness, wet:	100 micron [4 mils]
Overcoat interval, min:	40 approx. minute(s) at 20°C/68°F 60 minute(s) 10°C/50°F
Overcoat interval, max:	None
Safety:	Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult HEMPEL Safety Data Sheets and follow all local or national safety regulations.

SURFACE PREPARATION:	<p>Preparation: Always ensure all surfaces are clean, oil free and dry. Clean the surface and remove possible oil and grease with a suitable detergent and sand with dry abrasive paper. Carefully remove dust with fresh water.</p> <p>Uncoated surface: Prime prepared surface with HEMPEL'S LIGHT PRIMER 45551 and apply a tiecoat of HEMPEL'S UNDERWATER PRIMER 26030 whilst the surface is still tacky. Previously coated surface: Existing old self-polishing or traditional antifouling: Remove loose matter and contaminants by high pressure fresh water cleaning. Allow to dry. Existing old hard matrix antifouling or an unknown antifouling: High pressure fresh water clean, wet abrade, remove dust. Clean and dry the surface. If condition of previous antifouling is poor, seal with 1 coat of HEMPEL'S UNDERWATER PRIMER 26030.</p> <p>If previous antifouling is in general bad condition, it is recommended to remove previous coats and prime before applying antifouling.</p>
PRODUCT APPLICATION:	<p>Method: Mask other areas including the anodes prior to application. Shake well before use. Spray from a distance of 20 - 30 cm from surface. Apply one layer of the product at a time until a smooth, uniform surface is obtained. (minimum 4 coats) Shake can occasionally during use. Spray upside down at the end of spraying to clean the nozzle. Wear protective gloves/clothing and eye/face protection.</p> <p>If applying over HEMPEL'S LIGHT PRIMER 45551 or HEMPEL'S LIGHT PRIMER SPRAY 455EX, apply the spray whilst the surface is still tacky.</p>
APPLICATION CONDITIONS :	The surface must be completely clean and dry at the time of application and its temperature must be above the dew point to avoid condensation. Do not apply in direct sunlight. In confined spaces provide adequate ventilation during application and drying.
RECOMMENDED DETERGENT :	HEMPEL'S PRE-CLEAN 67602
PRECEDING COAT:	HEMPEL'S PROP PRIMER 101EX or HEMPEL'S UNDERWATER PRIMER 26030
SUBSEQUENT COAT:	None.
REMARKS:	
Stirring:	Mixing: Hold can in a vertical position and shake can vigorously until agitator ball is heard, then continue shaking for a further 2 minutes. Shake can occasionally during use. Spray upside down at the end of spraying to clean the nozzle.
Film thicknesses/thinning:	Note that application by spray can give a lower thickness per coat than other methods. Apply several coats using the whole can, to obtain the specified film thickness. The spray can should be held upright during application and only used when there is sufficient propellant.
Storage Conditions:	Exposure to air and temperature variances should be avoided. Avoid direct sunlight. Keep containers tightly sealed. Store at temperatures: 5°C/41°F - 35°C/95°F.
Launching:	Minimum: 24 hour(s) 20°C/68°F ; Maximum: 1 month
Overcoating:	No maximum overcoat interval, but after prolonged exposure to polluted atmosphere, remove accumulated contamination by high pressure fresh water cleaning and allow to dry before applying next coat.
Note:	HEMPEL'S ECOPOWER PROP 7446X
ISSUED BY:	HEMPEL A/S

7446X19990

This Product Data Sheet supersedes those previously issued.

For explanations, definitions and scope, see "Explanatory Notes" available on www.hempel.com. Data, specifications, directions and recommendations given in this data sheet represent only test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use of the Products herein must be determined exclusively by the Buyer and/or User.

The Products are supplied and all technical assistance is given subject to HEMPEL'S GENERAL CONDITIONS OF SALES, DELIVERY AND SERVICE, unless otherwise expressly agreed in writing. The Manufacturer and Seller disclaim, and Buyer and/or User waive all claims involving, any liability, including but not limited to negligence, except as expressed in said GENERAL CONDITIONS for all results, injury or direct or consequential losses or damages arising from the use of the Products as recommended above, on the overleaf or otherwise. Product data are subject to change without notice and become void five years from the date of issue.